

WE CLAIM:

- 3.1 CANCELLED [1. A crosslinked biocompatible material comprising at least one ionically crosslinked component; and at least one covalently crosslinked component, wherein the ionically crosslinked component is selected from a polysaccharide, a polyanion, or a polycation.
2. The crosslinked biocompatible material of claim 1 wherein the ionically crosslinked component is alginate.
3. The crosslinked biocompatible material of claim 2 wherein the alginate is a high G block alginate having at least 60%  $\alpha$ -L-guluronic acid.
4. The crosslinked biocompatible material of claim 3 wherein the  $\alpha$ -L-guluronic acid comprises at least 70%  $\alpha$ -L-guluronic acid.
5. The crosslinked biocompatible material of claim 2 further comprising a biologic encapsulated by the material.
6. The crosslinked biocompatible material of claim 5, wherein the material is effective to provide immunoprotection for the biologic in a physiological environment.
7. The crosslinked biocompatible material of claim 6, wherein the material provides immunoprotection of the biologic when xenotransplanted.
8. The crosslinked biocompatible material of claim 5, wherein the biologic is a biologically active material or a diagnostic marker.

09910663-071901

16. The crosslinked biocompatible material of claim 13, wherein the biologic is a biologically active material or a diagnostic marker.

17. The crosslinked biocompatible material of claim 16, wherein the biologically active materials are living cells selected from the islets of Langerhans, dopamine secreting cells, erythroprotein secreting cells, nerve growth factor secreting cells, hepatocytes, adrenaline/angiotensin secreting cells, parathyroid cells, or norepinephrine/metacephalin secreting cells.

18. The crosslinked biocompatible material of claim 16, wherein the biologically active material is a drug.]

19. A crosslinkable biocompatible mixture comprising:  
at least one ionically crosslinkable <sup>component; and</sup> ~~component, and~~ at least one covalently crosslinkable component, wherein the ionically crosslinkable component is selected from a polysaccharide, a polyanion, or polycation.

20. The crosslinkable biocompatible mixture of claim 19, wherein the ionically crosslinkable component is alginate.

21. The crosslinkable biocompatible mixture of claim 20, wherein the alginate is capable of ionically crosslinking by adding multivalent cations to the mixture.

22. The crosslinkable biocompatible mixture of claim 19, wherein the composition ratio between the ionically crosslinkable component and the covalently crosslinkable

b.1  
CANCELLED

09910663 071001  
T06T20" 8990T660

A.1

B.1

CANCELLED

component is effective for the stable crosslinking of the mixture, whereby a gelled encapsulation material is formed.]

**A.1 AMENDED** [23. The crosslinkable biocompatible mixture of claim 22, wherein the concentration and the molecular weight(s) of the covalently crosslinkable component are effective to provide immunoprotection to the encapsulated functional core once the mixture has been crosslinked.]

**A.2** 24. The crosslinkable biocompatible mixture of claim 23, wherein the mixture has an osmolarity and <sup>pH</sup>~~pH~~ compatible with the living tissue or cells.

**B.1 CANCELLED** [25. The crosslinkable biocompatible mixture of claim 24, wherein the osmolarity of the mixture is about 290 milliosmoles per kilogram and the pH is about 7.4.]

**B.2 AMENDED** [26. The crosslinkable biocompatible mixture of claim 23, wherein the concentration and molecular weight(s) of the covalently crosslinkable component are effective for the controlled release of the biologic or components of the biologic once the mixture has been crosslinked.]

27. A crosslinkable biocompatible mixture comprising: at least one ionically crosslinkable component; and at least one covalently crosslinkable component, wherein the covalently crosslinkable component is a polyalkylene oxide.

**B.3** 28. The crosslinkable biocompatible mixture of claim 27, wherein the polyalkylene oxide is <sup>acrylated and</sup> capable of covalently crosslinking by free radical polymerization.

29. The crosslinkable biocompatible mixture of claim 27, wherein the polyalkylene oxide is polyethylene glycol diacrylate.

5.1 [30. The crosslinkable biocompatible mixture of claim 27, wherein the composition ratio between the ionically crosslinkable component and the covalently crosslinkable component is effective for the stable crosslinking of the mixture, whereby a gelled encapsulation material is formed.]

0011563-071901  
A2 AMENDED [31. The crosslinkable biocompatible mixture of claim 30, wherein the <sup>concentration</sup>~~concentrator~~, and the molecular weight(s) of the covalently crosslinkable component are effective to provide immunoprotection to the encapsulated functional core once the mixture has been crosslinked.]  
A3

32. The crosslinkable biocompatible mixture of claim 31, wherein the mixture has an osmolarity and pH compatible with living tissue or cells.

3.1 CANCELLED [33. The crosslinkable biocompatible mixture of claim 32, wherein the osmolarity of the mixture is about 290 milliosmoles per kilogram and the pH is about 7.4.]

4 AMENDED [34. The crosslinkable biocompatible mixture of claim 31, wherein the concentration and molecular weight(s) of the covalently crosslinkable component are effective for the controlled release of the biologic or components of the biologic once the mixture has been crosslinked.]

4 AMENDED [35. A retrievable implantation material, comprising:

a crosslinked biocompatible macrocapsule comprising at least one ionically crosslinked component, and at least one covalently crosslinked component, whereby said macrocapsule encapsulates s microcapsule(s) of a biologic. ]

36. The retrievable implantation material of claim 35, wherein the macrocapsule provides immunoprotection to the encapsulated microcapsule(s) or biologic when xenotransplanted.

09910663-071901

A1-1 ADD CLAIM 37